

ATI Test Results Static Coefficient of Friction

This testing was based on ASTM D2394 criteria for wet and dry static coefficient of friction.

HERITAGE[™] DECKING

Average dry surface rating = 0.86

Average wet surface rating = 0.89

PASSPORT[®] DECKING

Average dry surface rating = 0.64

Average wet surface rating = 0.86

Heritage[™] and **Passport[®]** decking meet or exceed the American Disabilities Act (ADA) requirements for wet or dry static coefficient of friction.

These ratings place our decking at the upper levels of the category for alternative decking materials. This would include cellular PVC and also traditional wood/plastic composites.